

Exceed™ XP 8346PA

Performance Polymer

Product Description

Exceed™ XP 8346PA is an eXtreme Performance ethylene 1-hexene copolymer that offers easy processing and improved toughness for a versatility of use in cast film applications. TnPP is not intentionally added to Exceed™ XP 8346PA. Exceed™ XP 8346PA - when eXtreme Performance matters.

General

Availability ¹	<ul style="list-style-type: none"> ▪ Africa & Middle East ▪ Asia Pacific 	<ul style="list-style-type: none"> ▪ Europe ▪ Latin America 	<ul style="list-style-type: none"> ▪ North America
Additive	▪ EXCEED XP 8346PA: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes		
Applications	<ul style="list-style-type: none"> ▪ Barrier Food Packaging ▪ Cast Film 	<ul style="list-style-type: none"> ▪ Cast Flexible Film Packaging ▪ Diaper Backsheet 	<ul style="list-style-type: none"> ▪ Hygiene film
Form(s)	▪ Pellets		
Revision Date	▪ 10/14/2020		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.916 g/cm ³	0.916 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	3.5 g/10 min	3.5 g/10 min	ASTM D1238

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	960 psi	6.6 MPa	ASTM D882
Tensile Strength at Yield TD	930 psi	6.4 MPa	ASTM D882
Tensile Strength at Break MD	7000 psi	48 MPa	ASTM D882
Tensile Strength at Break TD	5500 psi	38 MPa	ASTM D882
Elongation at Break MD	500 %	500 %	ASTM D882
Elongation at Break TD	680 %	680 %	ASTM D882
Secant Modulus MD - 1% Secant	18000 psi	120 MPa	ASTM D882
Secant Modulus TD - 1% Secant	18000 psi	120 MPa	ASTM D882
Dart Drop Impact	290 g	290 g	ASTM D1709A
Elmendorf Tear Strength MD	280 g	280 g	ASTM D1922
Elmendorf Tear Strength TD	350 g	350 g	ASTM D1922
Puncture Force	8 lbf	36 N	ExxonMobil Method
Puncture Energy	34 in-lb	3.8 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	85	85	ASTM D2457
Haze	3.4 %	3.4 %	ASTM D1003

Legal Statement

Tris(nonylphenol)phosphite (TNPP) CAS#26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

EXCEED XP 8346PA can - in principle - be used in food contact applications in all EU Member States and in the USA (FDA). Migration or use limitations may apply. Please contact your ExxonMobil Chemical representative for more detailed information and/or actual compliance certification documents for the specific grade of interest.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Film (0.8 mil/20 micron) made from Exceed™ XP 8346PA on a 2.4"-3.4" cast film line at a 525-545°F (274-285°C) melt temperature, 77°F (25°C) chill roll temperature and 1050 fpm (320 m/min) line speed.

Exceed™ XP 8346PA Performance Polymer

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2021 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com